

# CORROSIONS-RESISTANT STEELS - AUSTENITIC STEELS AND NON MAGNETIC STEELS

## Available Product Variants

---

Plates

## Product Description

---

Austenitic chromium-nickel-silicon steel with excellent corrosion resistance in sulfuric acid and nitric acid. Components in the chemical industry and fertilizer plants.

## Process Melting

---

VID

## Applications

---

- > Components for Chemical plants (incl. LNG, FGD, Urea, LDPE, etc.)
- > Other Oil and Gas + CPI components
- > Tubular Products, Flanges, Fittings

## Chemical composition (wt. %)

---

C	Si	Mn	Cr	Mo	Ni	Cu
≤ 0,015	4,85 - 5,15	0,50 - 0,90	17,1 - 17,9	0,30 - 0,50	19,10 - 19,60	1,80 - 2,20

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

### voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25  
8605 Kapfenberg, AT  
T. +43/50304/20-0  
E. [info@bohler-edelstahl.at](mailto:info@bohler-edelstahl.at)  
<https://www.voestalpine.com/bohler-edelstahl/de/>

**voestalpine**

ONE STEP AHEAD.