

CORROSIONS-RESISTANT STEELS -AUSTENITIC STEELS AND NON MAGNETIC STEELS

| | | | _ | | |
|------------|-----|-------|-------|-----------|---|
| An | nli | icati | on Se | gments | Ċ |
| $\neg ho$ | | Cati | | gillerics | , |

Available Product Variants

| Long Products' | ÷ |
|----------------|---|
|----------------|---|

Product Description

BÖHLER A750 is an austentic, corrosion and heat-resistant chromium nickel steel, niobium stabilized and solution treated. It have been

used typically for parts requiring good corrasion resistance and which will be subjected to elevated temperatures during fabrication or in service and for parts requiring oxidation resistance up to 1500 °F (816°C), but usage is not limited to such applications. Compared to common 13% chromium steel, it offers higher corrosion resistance at lower strength and good weldability. No post-weld heat treatment required. The steel is resistant to atmospheric corrosion and the action of steam, water and acid as well as alkaline solutions. For optimum resistance, surfaces should be pickled or polished. Cold forming properties are very good. The steel is capable of taking a mirror finish.

Process Melting

Airmelted

Applications

> Other Aerospace Components

> Aerospace

Technical data

| Material designation | | |
|----------------------|-----|--|
| 1.4546 | SEL | |
| X5CrNiNb18-10 | EN | |
| Z6CnNb1810 | | |
| S34700 | UNS | |

| Standards | | |
|-----------|------------------|-----|
| | 5646 | AMS |
| | S130 970 Pt.3 | BS |
| | | |



^{*} Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).



CORROSIONS-RESISTANT STEELS -AUSTENITIC STEELS AND NON MAGNETIC STEELS

Chemical composition (wt. %)

| С | Si | Mn | P | S | Cr | Мо | Ni | Cu | Со | Nb |
|--------------|--------------|-----------|---------------|---------------|----------------|-----------|---------------|-----------|-----------|--------------|
| max. 0.08 | max. 1.00 | max. 2.00 | max. 0.040 | max. 0.030 | 17.00 to 19.00 | max. 0.75 | 9.00 to 12.00 | max. 0.75 | max. 1.00 | 10xC to 1.10 |

Related to AMS5646

Delivery condition

| Solution annealed | | | | | |
|---|---|--|--|--|--|
| Tensile Strength (MPa) | min. 517 bars above 12.7 mm diameter | | | | |
| Yield Strength (MPa) min. 207 bars above 12.7 mm diameter | | | | | |
| Solution annealed | | | | | |
| Tensile Strength (MPa) | 586 to 862 wire | | | | |
| Solution annealed | | | | | |
| Hardness (HB) | 140 to 255 bars up to 50.8 mm diameter, inclusive | | | | |
| Solution annealed | | | | | |
| Hardness (HB) | max. 255 bars above 50.8 mm diameter | | | | |

Round Bars and Wire Rod (if any)

| Diameter mm | | er | MOQ ex mill | Length | | ıth | Tolerance | |
|----------------|---|--------|-------------|--------|---|------|-----------|--|
| | | | kg | | m | | | |
| ROLLED | | | | | | | | |
| 5.01 | - | 12.49 | 800 | 3.00 | - | 4.00 | IT h/k 11 | |
| 12.50 | - | 55.00 | 950 | 3.00 | - | 4.00 | IT h/k 11 | |
| 55.01 | - | 69.00 | 1,200 | 3.00 | - | 4.00 | IT h/k 11 | |
| 69.01 | - | 72.00 | 1,000 | 3.00 | - | 4.00 | IT h/k 11 | |
| 72.01 | - | 82.00 | 1,150 | 3.00 | - | 4.00 | IT h/k 11 | |
| 82.01 | - | 120.00 | 1,300 | 3.00 | - | 4.00 | IT h/k 11 | |
| 120.01 | - | 140.00 | 1,300 | 3.00 | - | 5.00 | IT h/k 14 | |
| | | · | FOI | RGED | | | | |
| 140.01 | - | 220.00 | 1,400 | 2.00 | - | 5.00 | IT h/k 14 | |

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

