

CO-BASE ALLOYS

Application Segment	S		
Oil & Gas/CPI			
Available Product Va	riants		
Long Products			

Product Description

BÖHLER L035 is a 35-cobalt-35-nickel-20-chromium-10-molybdenum wrought alloy (UNS R30035) in the form of bar material.

It is a vacuum induction melted (VIM) and vacuum arc remelted (VAR) superalloy. This alloy is typically used in the oil and gas and chemical industries where a combination of high strength, good fatigue resistance. toughness, ductility and exceptionally good corrosion resistance after subsequent ageing is required. However, its use is not limited to such

applications. BOHLER L035 is a nickel-cobalt based multiphase alloy system with a unique combination of properties e.g. extremely high strength, toughness, ductility and excellent corrosion resistance. The alloy can be strengthened and aged in the factory to achieve strength values of over 260 ksi (1793 MPa) and stress corrosion cracking (SCC) resistance even in hydrogen sulphide. The BOHLER L035 alloy resists pitting sulphuric acid).

Process Melting

VIM + VAR

Applications

- > Oil & Gas / CPI
- > Other Oil and Gas + CPI components

> Other Components

> Medical Industry

> Medical

Technical data

Material designation		Standards	
MP35N	Market grade	5844	AMS
2.4999	SEL		

Chemical composition (wt. %)

С	Si	Mn	Р	s	Cr	Мо	Ni	Со	Ti	Fe
max. 0.025	max. 0.15	max. 0.15	max. 0.015	max. 0.010	19.00 to 21.00	9.00 to 10.50	33.00 to 37.00	REM	max. 1.00	max. 1.00

Refers to AMS 5844.





Delivery condition

Solution annealed + cold worked	
Hardness (HRC)	min. 38

Round Bars and Wire Rod (if any)

Diameter*				
mm				
ROLLED				
5.00	- 13.50			
12.50	- 31.75			

* Diameter 5.00 - 13.50 mm available as Wire Rod.

Diameter 12.5 - 31.75 mm round bars.

Further information on MOQ, lengths and tolerances on request.

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0

E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

