

NI-BASE ALLOYS

Application Segments

Oil & Gas / CPI

Available Product Variants

Long Products*

Semi-Finished Products / Billet

Plates

Open Die Forgings

Product Description

BÖHLER L718 API (UNS N07718) is a high-strength, corrosion-resistant nickel chromium iron molybdenum material that offers high strength and excellent corrosion resistance, particularly in H2S and CO2 environments. It is a precipitation hardenable alloy, the precipitation hardening effect is mainly achieved by additions of Niobium, Titanium and Aluminium. The ease and economy with which BÖHLER L718 API can be fabricated, combined with good tensile, fatigue, creep, and rupture strength, have resulted in its use in a wide range of applications. It have been widely recognised by the oil industry and it is now widely used in this field. BÖHLER L718 API offers outstanding weldability with resistance to post-weld cracking. It can be used in high temperatures as it maintains strength at elevated temperatures. Several conditions of BÖHLER L718 API are available and it is offered to the NACE/API 6A CRA versions at 120 /140 ksi min yield as well as the 150 ksi high strength version. All tempers are suitable for sour service and can be used for pressure containing and pressure controlling equipment in corrosive environments. Typical applications include packers, pumps, connectors, and fasteners as well as gate valves, choke stems, tubing hangers and fire safe valves but also multiple downhole drilling & completions, nuclear and surface applications.

Process Melting

VIM + VAR

Applications

- > Oil & Gas / CPI
- > Wellhead, X-mas trees and Manifolds (incl. Tubing hangers), BOPs
- > Flowlines & Connectors
- > Well Logging Tools
- > CPI (incl. LNG, Urea)

- > Well Completion Tools
- > Other Oil and Gas + CPI components
- > Tubular Products, Flanges, Fittings
- > Components for Chemical plants (incl. LNG, FGD, Urea, LDPE, etc.)
- > Heat Exchanger

- > Fasteners, Bolts, Nuts
- > Drilling tools and components
- > Valves and Actuators
- Components for underground construction (drilling, shafts, etc.)
- > Oil & Gas, CPI & Renewables

Technical data

Material designation	
Alloy 718API	Market grade
N07718	UNS

Standards				
API 6A CRA				
NACE MR0103 / ISO 17945	Others			
NACE MR0175 / ISO 15156				



^{*} Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).



Chemical composition (wt. %)

С	Si	Mn	P	S	Cr	Мо	Ni	Cu	Co	Ti	Al	Nb	В	Fe	Pb	Bi	Ca	Mg	Se
max. 0.045	max. 0.35	max. 0.35	max. 0.010	max. 0.010	17.0 to 21.0	2.80 to 3.30	50.0 to 55.0	max. 0.23	max. 1.00	0.80 to 1.15	0.40 to 0.60	4.87 to 5.20	max. 0.0060	REM	max. 0.0010	max. 0.00005	max. 0.0030	max. 0.0060	mo 0.0

Refers to API Standard 6A CRA N07718 | Nb + Ta 4.87 to 5.20

Delivery condition

Solution annealed + precipitation hardened 120k				
Hardness (HRC) 32 to 40				
Tensile Strength (MPa)	min. 1,034			
Yield Strength (MPa)	827 to 1,000			

Solution annealed + precipitation hardened | 140k

Hardness (HRC)	34 to 44
Tensile Strength (MPa)	min. 1,138
Yield Strength (MPa)	965 to 1,034

Solution annealed + precipitation hardened | 150k

	· · · · · · · · · · · · · · · · · · ·
Hardness (HRC)	35 to 45
Tensile Strength (MPa)	min. 1,207
Yield Strength (MPa)	1,034 to 1,207

Round Bars and Wire Rod (if any)

Diameter*

mm

111111					
ROLLED					
5.00	- 13.50				
12.50	- 101.60				
FORGED					
101.70	- 355.60				

^{*} Diameter 5.00 - 13.50 mm available as Wire Rod.

Diameter 12.5 - 101.60 mm round bars.

Variant 140k is available in forged products only

More information regarding MOQ, lengths and tolerances upon request. Flat bars on request.

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

