

Application Segments

CORROSION RESISTANT STEELS - MARTENSITIC, SEMIMARTENSITIC AND FERRITIC STEELS

Automotive							
Available Product Varia	ants						
Long Products							
Product Description							
BÖHLER N114 is a modified resistance. Due to the high su N114 has very good hot and o	alphur content, th	ne material can be machine	netic properties, namely very low coercive force and high electrical ed very well, for example on automatic machining centres. BÖHLER				
Used for stainless parts for mechanical and electrical engineering, e.g. solenoid valves, pistons, back-locking parts, pole cores, shields and magnetic armatures.							
Delivery condition annealed ex works. A final annealing treatment for magnetic properties must be carried out after cold forming, e.g. extrusion, upsetting or extensive machining processes.							
Process Melting							
Airmelted							
Applications							
> Automotive > Injection Components		Motorsport industry Valves and Actuators	> Civil and mechanical engineering				
Technical data							
Material designation		Standards					
BÖHLER Trademark	Market grade	10088-1	EN ISO				



CORROSION RESISTANT STEELS - MARTENSITIC, SEMI-MARTENSITIC AND FERRITIC STEELS

BÖHLER N114

Chemical composition (wt. %)

С	Si	Mn	Р	S	Cr	Al
max. 0.08	max. 1.25	max. 1.00	max. 0.040	max. 0.23	12.00 to 14.00	0.20 to 0.80

Refers to EN-ISO 10088-1, 1.4002 modified

Delivery condition

Annealed Dimension max. 60 mm						
Hardness (HB)	120 to 180					
Tensile Strength (MPa)	400 to 600					
Others Annealed + cold worked						
Hardness (HB)	150 to 220					
Tensile Strength (MPa)	450 to 650					

Round Bars and Wire Rod (if any)

Diameter*

mm

ROLLED					
5.00	-	13.50			
12.50	-	50.00			

^{*} Diameter 5.00 - 13.50 mm available as Wire Rod.

Diameter 12.5 - 50 mm round bars.

More information regarding MOQ, lengths and tolerances upon request.

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at

https://www.voestalpine.com/bohler-edelstahl/de/

