

# ENGINEERING STEELS - HEAT TREATABLE AND NITRIDING STEELS

## Available Product Variants

Plates

## Product Description

Böhler V330SH - Alloy 4130

## Process Melting

VID + Ingot casting

## Applications

- > Other Aerospace Components
- > Structural parts (Aerospace)

## Technical data

Material designation		Standards	
Alloy 4130	Market grade	6345	AMS
1.7220	SEL	6350	

## Chemical composition (wt. %)

C	Si	Mn	Cr	Mo
0.32	0.3	0.5	1.1	0.2

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG  
Mariazeller Straße 25  
8605 Kapfenberg, AT  
T. +43/50304/20-0  
E. info@bohler-edelstahl.at  
<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.