

NI-BASE ALLOYS

Available Product Variants

Product Description

Nickle-Chromium-Iron alloy with added Titanium, used for components in steam and gas turbines.

Applications

> Other Power Generation Components

Technical data

Material designation		
2.4951	SEL	
2.4630	SEL	
N06075	UNS	
Alloy 75	Market grade	

Chemical composition (wt. %)

С	Cr	Ni	Со	Ti	Al	Fe
0.07	19.5	Rest	2.5	0.3	0.2	5

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

