

HEAT TREATABLE STEELS AND PRECIPITATION HARDENING STEELS

Available Product Variants

Plates

Product Description

Carrier Plates for the production of technical und decorative laminates.

Properties

Tolerance ground, tensile strength in annealed condition max. 750 N/mm², cold rolled to 30 - 35 HRC

Applications

> Press Plates

Technical data

Material designation	
1.7225	SEL
AISI: 4140	AISI

Chemical composition (wt. %)

С	Cr	Мо
0.4	1.1	0.2

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

